



# Reliance Supply Company

## Coloron Solid Color Sealer/Stain for Concrete

Coloron is a solvent based concrete sealer designed to penetrate concrete. Coloron has been a standard in the industry since the 1960's for interior and exterior concrete protection. Coloron's glossy finish is highly resistant to acids, oils, and tire marking.

### Directions

Stir product. Surfaces must be clean and dry before sealing. Coloron's performance is directly related to how thoroughly the surface is prepared. All grease, oil and potential contaminants must be removed. Concrete should cure a minimum of 28 days before sealing. Read label instructions carefully. Smooth concrete must be etched. Cobble Clean and Cobble Prep may be used for specific cleaning situations. Two thin coats(2 dry mils) provide the best results. Testing the product on your surface is always recommended to ensure desired results.

### Dry Times

Dry to touch: 30 minutes  
Light traffic and recoat: 3 to 4 hours  
Full cure: 36 to 48 hours

### Packaging & Unit Shipping Weight

1- gal cans- 4 gal. per case- 40 cases per pallet: 33 lbs per case  
5- gal pails- 36 pails per pallet: 45 lbs per pail

**Warning:** Coated surfaces may become slippery. Reliance Supply's non-skid additive should be incorporated in this situation. However, it is the sole responsibility of the applicator to determine whether a non-skid additive should be incorporated and if it will work for their job .

Use with adequate ventilation. Product contains Xylene.

All Reliance Supply Company products are manufactured with the finest raw materials. The shelf life is 12 months from date of purchase when maintained in protected storage of 50F to 90F. It is the applicator's responsibility to determine the appropriate use of the product. All recommendations and suggestions are made without guarantee, since the conditions of use are beyond our control.

### Characteristics and Technical Data

% Solids by Wt.(+/- 3%)	40%
Gardner Gloss @ 60	89
Flash Point	116F
WT./GL.:	8.8lbs
Coverage:	200-300 SqFt./Gl. @ 2 mil DFT
Clean Up:	Xylene or Lacquer Thinner
VOC's	600G/L